

**Fibreglass net combined with specially designed net surface treatment****Application**

- Indoor and outdoor
- Mainly prescribed in our layers with thicker structure ( + 10mm )
- In plaster layers
- In cementing
- In crack-sensitive substrates
- ...

**Properties**

- Made of E Glass.
- Fitted with alkali-resistant coating.
- High tensile strength.
- Dimensionally stable.
- CE marking.

**Directions**

- Insert the fibreglass net into an already applied wet layer of the product to be used.
- Push the fibreglass net well into the applied layer. Do this from the middle to the outside.
- The overlapping of different parts of glass fibre net is at least 10 cm to ensure continuity of reinforcement.
- Recommendation for use in our systems available from your Technical Advisor.

**Technical characteristics**

Mass per unit area	138 g/m <sup>2</sup>
Mesh opening	10 by 8 mm
Thickness	0,67 mm
Tensile strength in supplied condition	2000 – 2100 N/50 mm
Elongation in supplied condition	max 3,5%
Tensile strength after 28 days alkaline conditioning	1350 N/50 mm
elongation after 28 days alkaline conditioning	max 3,5%

**Quantity to use**

0,9 meter/m<sup>2</sup>

**Packaging**

Roll (length 50 m, width 100 cm)

**Safety information – Transport – Handling and storage - Waste**

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

**Transport and storage**

Store the product and its packaging dry and protect against moisture.

**Storage life**

No specific expiration date when stored as directed.

**Considerations**

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.